



DETAILED SPECIFICATION

UreconRed[®] for below grade warm water systems

1) General

The pipe shall be insulated using the U.I.P.[®] factory insulation process, as supplied by Urecon Ltd. with red UV inhibited polyethylene jacket. Insulation of associated joints, fittings and accessories shall be as per Urecon's recommendations based on the size and type of pipe involved. The product shall be manufactured in accordance to ISO 9001-2000 Standards.

2) Pipe Preparation

Pipe shall be cleaned of surface dust or dirt and treated, if necessary, to insure adhesion of the foam to the pipe surface.

3) Insulation

- a) Material: rigid polyurethane foam, factory applied.
 - b) Thickness: nominal 25 to 50mm (1 to 2 in) depending on pipe diameter
 - up to 200mm \varnothing (8 in \varnothing) nominal pipe @ 25 mm (1 in) thick
 - 225mm \varnothing (9 in \varnothing) to 350mm \varnothing (14 in \varnothing) nominal pipe @ 37 mm (1.5 in) thick
 - 375mm \varnothing (15 in \varnothing) to 600mm \varnothing (24 in \varnothing) nominal pipe @ 50 mm (2 in) thick
- Other thicknesses available upon request
- c) Density: (ASTM D 1622) 35 to 46 kg/m³ (2.2 to 3.0 lbs/ft³).
 - d) Closed cell content: (ASTM D 6226) 90%, minimum.
 - e) Water absorption: (ASTM C272) 4.0% by volume.
 - f) Thermal conductivity: (ASTM C518) 0,020 to 0,026 W/m °C (0.14 to 0.17 Btu • in/ft² • hr • °F).

4) System Properties

- a) System compressive strength: (modified ASTM D 1621 with 0,42mm (15 mil) red polyethylene jacket, approximately 414 to 552 kPa (60-80 lbs/in²) system compressive strength, varies with pipe diameter; other jacket thicknesses are available upon request.
- b) Temperature limitations: -in service to 93°C (200°F)

5) Outer jacket characteristics

- a) Jacket material: UV stable red polyethylene specially formulated and applied waterproof for below grade applications; may be used above grade in UV protected conditions.
- b) Sealant: butyl rubber and resin.
- c) Jacket thickness: insulation diameter
 - up to 380mm (14.95 in) @ 0,42mm (15 mils)
 - 381mm (15.0 in) to 583mm (22.95 in) @ 0,51mm (20 mils)
 - 584mm (23.0 in) and over @ 1,02mm (40 mils)
- d) Minimum elongation: (ASTM D 1000) 300%, 6 month test.
- e) Service temperature range: in service to 93° C (to 200°F)
- f) Tensile strength: (ASTM D-1000) 6, 83 kg/cm wide (38 lbs/in wide).



6) Insulated pipe joints

a) Butt-fused and welded joints (plain end pipe)

Insulated pipe joints shall be completed using pre-fabricated rigid polyisocyanurate or urethane half shells and sealed with the application of 0,25mm (10 mil) X 50mm (2 in) wide red polyethylene hand roll tape, as supplied by Urecon. Tape shall be applied in such a manner as to yield a minimum of 75 mm (3 in) overlap on either side of the joint.

b) Bell x spigot joints

Insulated pipe joints shall be sealed with the application of either 0,25mm (10 mil) X 50mm (2 in) wide red polyethylene hand roll tape, as supplied by Urecon. Tape shall be applied in such a manner as to yield a minimum of 75 mm (3 in) overlap on either side of the joint.

7) Insulation kits for fittings.

Insulation kits for fittings shall consist of rigid polyisocyanurate or urethane foam insulation supplied with 0,25mm (10 mil) X 50mm (2 in) wide red polyethylene hand roll tape as supplied by Urecon. Tape shall be applied in such a manner as to yield a minimum of 75 mm (3 in) overlap on either side of the joint, and shall be consistent with what is used at the joints.

a) Rigid Polyisocyanurate or polyurethane foam insulation

- .1 Density: (ASTM D1622) 27 to 32 kg/m³ (1.7 to 2.0 lbs/ft.³).
- .2 Compressive strength: (ASTM D1621) 131 to 158 kPa (19 to 23 lbs/in.²).
- .3 Closed cell content (ASTM D 6226) 90%, minimum.
- .4 Water absorption: (ASTM C272) 4.0% by volume.
- .5 Thermal Conductivity: (ASTM C 518) 0,027 W/m °C (0.19 Btu • in/ft² • hr • °F).
- .6 Thickness: to match pipe insulation thickness.

Note: Physical characteristics are nominal and may vary depending on pipe type and diameter